

Technical Data

Medium Grained Graphite

Extract from the Olmec programme of extruded grades



Grade	Bulk Density (g/cm ³)	Porosity (%)	Spec. el. Resistance (Ω mm ² /m)	Compressive Strength (N/mm ²)	Bending Strength (N/mm ²)	Ash Content (%)	Thermal Expansion Coefficient (10 ⁻⁶ /K)	Thermal Conductivity (W/m K)	Max. Grain Size (mm)	Standard Sizes (mm)
MCCA	1.78 - 1.82	11 - 14	6 - 8	60	38 - 42	<0.1	2.0 - 2.5	120 - 140	0.35	Ø 3 .. 9
MCCA	1.76 - 1.80	12 - 15	6 - 8	35 - 40	20 - 25	<0.1	1.8 - 2.5	120 - 140	0.6	Ø 10 .. 25
MCCA	1.72 - 1.75	14 - 17	6 - 8	30 - 40	20 - 25	<0.1	1.8 - 2.5	120 - 140	0.6	Ø 30 .. 105
MCCA	1.70 - 1.73	16 - 19	6 - 8	26 - 32	17 - 20	<0.1	1.6 - 2.2	120 - 140	0.8	Ø 110 .. 700
MCCA	1.66 - 1.73	18 - 20	5 - 8	22 - 28	16 - 19	<0.1	1.6 - 2.2	120 - 140	0.8	Plates**
MRCM	1.76 - 1.80	12 - 15	4 - 5	50	25	<0.25	1.3 - 1.6	150 - 180	2	Ø 200 .. 300
VDN	1.67 - 1.73	17 - 20	5 - 7	23 - 28	10 - 14	<0.8	1.5 - 2.0	130 - 150	10 - 20	Ø 300 .. 600

* In direction of extrusion

** Sizes in mm: 108 x 495 x 1100, 1800; 140 x 428 x 1100;
 120 x 330 x 1100; 170 x 375 x 1100
 400 x 400 x 1800 500 x 500 x 1800
 other sizes and lengths on demand

All values are average values / typical ranges

Olmec Advanced Materials Ltd
 12 Terminus Road
 Sheffield
 S7 2LH, UK

GB VAT No. 570 6797 06
 Company Reg No. 247 6257



026
 Certificate No. 1644/98

Tel: +44 (0) 114 236 1606
 Fax: +44 (0) 114 262 1202
 Email: info@olmec.co.uk
 Website: www.olmec.co.uk